


STEAM/AL



IT IMPIEGO

Tubo in gomma cord idoneo per mandata di acqua calda e vapore saturo con pressione massima 6 bar 165° in impieghi dove sia richiesta atossicità per i prodotti convogliati.

Normative di riferimento: **DM 21/3/73 e 18/6/79 + F.D.A. 1935/2004 (MOCA)**

- **TEMPERATURA:** -40°C +120°C

STRUTTURA

- **Sottostrato:** liscio in gomma EPDM bianca alimentare resistente al calore.
- **Rinforzi:** inserzioni di fibre sintetiche ad alta resistenza.
- **Copertura:** in gomma EPDM blu resistente all'abrasione, al calore e agli agenti atmosferici. Stabilità del colore.
- **Superficie:** liscia ad impressione tela, scritta bianca.
- **Marcatura:** listino scritta bianca "H.T. - STEAM W.P 6 BAR - HOT WATER WP 15 BAR - +120°C - F.D.A."

EN APPLICATION

Softwall rubber hose suitable for hot water and saturated steam up to maximum working pressure of 6 bar 165° mix used where an atoxic hose is required.

Standards: **DM 21/3/73 e 18/6/79 + F.D.A. 1935/2004 (MOCA)**

- **TEMPERATURE RANGE:** -40°C +120°C

CONSTRUCTION

- **Tube:** white, smooth, heat resistant food quality EPDM rubber.
- **Reinforcement:** high strength synthetic textile plies.
- **Cover:** blue, abrasion, heat and weathering resistant EPDM rubber. Non staining.
- **Surface:** smooth fabric finished, white lettering.
- **Branding:** white transfer tape lettering "H.T. - STEAM W.P 6 BAR - HOT WATER WP 15 BAR - +120°C - F.D.A."

DIAMETRO INTERNO INSIDE DIAMETER		DIAMETRO ESTERNO OUTSIDE DIAMETER		PESO TEORICO WEIGHT		PRESS. ESERCIZIO WORKING PRESSURE		PRESSIONE SCOPPIO BURST PRESSURE		LUNGHEZZA LENGTH	
mm	inch	mm	inch	kg/mt	lbs/ft	bar	psi	bar	psi	mt	ft
13	1/2"	23	29/32"	0.37	0.25	6/15	90/225	60/45	900/675	40	131
16	5/8"	26	1.1/32"	0.43	0.29	6/15	90/225	60/45	900/675	40	131
19	3/4"	30	1.1/16"	0.55	0.37	6/15	90/225	60/45	900/675	40	131
25	1"	37	1.15/32"	0.75	0.50	6/15	90/225	60/45	900/675	40	131

Altri diametri e/o pressioni realizzabili su richiesta - Le caratteristiche e i dati tecnici possono essere modificati senza preavviso.

Other diameters and/or pressures are feasible upon request - The characteristics and technical data could be changed without warning.