

# TRECOIL/CO

H.T.- ECO FUEL - SP482 - B10 TGB/FA DIN 73379/2A TYPE B

## IT IMPIEGO

**Tubo in gomma trecciato in cotone** idoneo per mandata di olii minerali, lubrificanti, carburanti, benzine ecologiche e acqua emulsionata di raffreddamento. Impiegato sui motori a combustione interna.

*Normative di riferimento: DIN 73379, tipo B.*

- **TEMPERATURA:** -40°C +90°C

## STRUTTURA

- **Sottostrato:** liscio in gomma nera NBR resistente a prodotti petroliferi con un contenuto aromatico non superiore al 50%.
- **Rinforzi/Copertura:** treccia di filato di cotone nero vulcanizzata e impregnata con soluzione di neoprene, che rende il tubo autoestinguento e antiputrescibile.
- **Superficie:** trecciata.
- **Marcatura:** ad inchiostro "H.T.- ECO FUEL - SP482 - B10 TGB/FA DIN 73379/2A TYPE B".

**Disponibile su richiesta:**

**TRECOIL/CO/ZINC:** con rivestimento in calza acciaio zincato.

## EN APPLICATION

**Cotton braided rubber hose** suitable for delivery of mineral oils, lubricants, unleaded fuel and common cooling liquids. Used for internal combustion engines.

*Standards: DIN 73379, type B.*

- **TEMPERATURE RANGE:** -40°C +90°C

## CONSTRUCTION

- **Tube:** black, smooth, petroleum products up to 50% aromatic content resistant NBR rubber.
- **Reinforcement/Cover:** braided black cotton thread and dipped in a neoprene selfextinguishing solution.
- **Surface:** braided.
- **Branding:** ink marking "H.T.- ECO FUEL - SP482 - B10 TGB/FA DIN 73379/2A TYPE B".

**Available on request:**

**TRECOIL/CO/ZINC:** galvanized steel wire braided cover.

DIAMETRO INTERNO INSIDE DIAMETER		DIAMETRO ESTERNO OUTSIDE DIAMETER		PESO TEORICO WEIGHT		PRESS. ESERCIZIO WORKING PRESSURE		PRESS. SCOPPIO BURST PRESSURE		RAGGIO CURVATURA BENDING RADIUS		LUNGHEZZA LENGTH	
mm	inch	mm	inch	kg/mt	lbs/ft	bar	psi	bar	psi	mm	inch	mt	ft
3	1/8"	7	5/8"	0.04	0.03	10	150	30	450	25	0.98"	50	164
4	1/6"	8	5/16"	0.05	0.03	10	150	30	450	35	1.38"	50	164
5	3/16"	10	3/8"	0.08	0.05	10	150	30	450	40	1.57"	50	164
6	1/4"	11	7/16"	0.10	0.07	10	150	30	450	50	1.97"	50	164
6	1/4"	13	1/2"	0.14	0.09	10	150	30	450	50	1.97"	50	164
7	5/18"	13	1/2"	0.13	0.09	10	150	30	450	55	2.17"	50	164
7.5	5/16"	14.5	19/32"	0.16	0.11	10	150	30	450	60	2.36"	50	164
8	5/16"	13	1/2"	0.11	0.07	10	150	30	450	65	2.56"	50	164
8	5/16"	15	19/32"	0.16	0.11	10	150	30	450	65	2.56"	50	164
10	3/8"	15	19/32"	0.14	0.09	10	150	30	450	80	3.15"	50	164
10	3/8"	17	21/32"	0.19	0.13	10	150	30	450	80	3.15"	50	164
13	1/2"	20	25/32"	0.24	0.16	10	150	30	450	130	5.12"	50	164
16	5/8"	23	29/32"	0.28	0.19	10	150	30	450	160	6.30"	50	164
19	3/4"	27	1.1/16"	0.38	0.26	10	150	30	450	190	7.48"	50	164
25	1"	34	1.11/32"	0.50	0.34	10	150	30	450	250	9.84"	50	164

Altri diametri e/o pressioni realizzabili su richiesta - Le caratteristiche e i dati tecnici possono essere modificati senza preavviso.

Other diameters and/or pressures are feasible upon request - The characteristics and technical data could be changed without warning.